



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 731 190 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
06.05.1999 Bulletin 1999/18

(51) Int Cl.⁶: C23C 16/26, C23C 16/02

(21) Application number: 96200315.8

(22) Date of filing: 12.02.1996

(54) Process for the formation of carbon coatings

Verfahren zur Abscheidung von Kohlenstoffschichten

Procédé de fabrication de couches de carbone

(84) Designated Contracting States:
DE FR GB

(30) Priority: 08.03.1995 US 401110

(43) Date of publication of application:
11.09.1996 Bulletin 1996/37

(73) Proprietor: GENERAL MOTORS CORPORATION
Detroit Michigan 48202 (US)

(72) Inventors:

- Oul, Xiaohong c/o Shanghai Room 3-220
Detroit Michigan 48202 (US)
- Mantese, Joseph V.
Troy, Michigan 48063 (US)
- Elmoursi, Alaa A.
Troy Michigan 48098 (US)
- Hamdi, Aboud H.
Warren, Michigan 48090-1472 (US)

- Wood, Blake P.
Los Alamos, New Mexico 87544 (US)
- Walter, Kevin C.
Los Alamos, New Mexico 87544 (US)
- Nastasi, Michael A.
Española, New Mexico 87532 (US)
- Malaczynski, Gerard W.
Bloomfield Hills, Michigan 48304 (US)

(74) Representative: Manitz, Finsterwald & Partner
Postfach 22 16 11
80506 München (DE)

(56) References cited:
EP-A- 0 537 062 FR-A- 2 590 594
FR-A- 2 596 775 US-A- 5 237 967

- PATENT ABSTRACTS OF JAPAN vol. 014, no.
334 (C-0742), 18 July 1990 & JP-A-02 122075
(NIPPON STEEL CORP; OTHERS: 01), 9 May
1990,

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Technical Field

[0001] This invention pertains to a practice for the formation of adherent, hard, low friction carbon coatings. In a specific, illustrative application, this invention pertains to the formation of such diamond-like carbon coatings on silicon-containing aluminum alloy articles in a process that is amenable to high volume usage, especially for irregularly-shaped articles such as automobile parts.

Background of the Invention

[0002] In a continual effort to reduce weight and improve the fuel efficiency of automotive vehicles and the like, engineers seek to substitute lighter (and usually softer) materials such as aluminum and magnesium alloys for the more dense and more scuff- and wear-resistant iron and steel alloys that are widely used. Often the substitution of aluminum in engines and other powertrain component applications exposes them to sliding contact with other aluminum parts. While aluminum alloy parts are strong, they are susceptible to wear and scuffing when they rub on each other. Their surface properties are such that they must be adequately lubricated in such applications. For example, it is desirable to employ aluminum alloy pistons in an aluminum alloy engine block. In normal warmed-up engine operation, a film of oil can be maintained between each reciprocating piston and its cylinder wall. However, during cold start and other situations, if the oil film has not been established, aluminum surfaces in sliding engagement will soon scuff. Material from the piston or the engine block surface is transferred to the opposite member, which causes additional scuffing and tearing and failure of the parts.

[0003] Thus, where aluminum alloy pistons and engine blocks are used in automotive engine applications, it is the practice to provide iron liners in the cylinder walls of the aluminum block. The aluminum pistons then engage iron liners, and even during cold starts, no scuffing or undue wear occurs. However, the manufacture and placement of iron liners in the cylinder bores of an aluminum engine block represent an undesirable additional expense and weight.

[0004] The properties of certain amorphous hydrogen-containing carbon deposits have been investigated as protective layers on surfaces that are to be subjected to wear or scuffing. When suitably formed, these carbonaceous materials are found to be extremely hard and wear resistant, and they are sometimes called diamond-like carbon. Once recognized, it has been suggested that carbon and other hard coatings could be used on aluminum alloy components in sliding engagement with other aluminum alloy components in automotive powertrain environments. See, for example, U.S.

Patents 5,237,967 and 5,249,554. However, the difficulty in utilizing such hard coatings on automotive components is that the complexity of the process, the multiplicity of material layers and the cost of forming adherent and uniform coatings on workpieces of complex shape has been too high. In other words, the processing has been too slow and too cumbersome.

[0005] The present invention provides an efficient process for applying adherent, hard and low friction amorphous carbon coatings to the surfaces of three-dimensional workpieces of suitable materials susceptible to carbon ion implantation. The present process is particularly useful on workpieces of aluminum alloys, ferrous metal alloys and other alloys capable of forming intermetallic carbides. It is a further object to provide a method of providing such coatings that strongly adhere to the workpiece substrate. It is a still further object of the present invention to provide a method that is efficient and practical enough for automotive manufacturing requirements.

[0006] In accordance with this invention, these and other objects and advantages are accomplished as follows.

Summary of the Invention

[0007] A preferred and illustrative application of this process is in the formation of adherent, diamond-like carbon coatings on aluminum alloys. For purposes of illustration, the practice of the invention will be described in connection with aluminum alloy A390, a commercial casting alloy containing, nominally by weight, 17 percent silicon, 0.8 percent iron and 4.5 percent copper. Such hypereutectic aluminum-silicon alloys are representatives of several aluminum alloys suitable for the casting of pistons and other engine and powertrain components.

[0008] The practice of the process involves implanting carbon into the surfaces of the aluminum-silicon workpiece(s) to form carbides in a shallow layer to a suitable depth of, e.g., 75 to 150 nanometers. The workpiece(s) may be of any desired configuration. Prior to ion implantation, oxygen atoms must be removed from the surface regions of the workpiece to permit silicon carbide and/or aluminum carbide formation. The surface oxides can be suitably decomposed and oxygen atoms removed by bombardment with argon ions or other chemically inert ions. Other oxide removal processes could be used.

[0009] Argon or other suitable inert gas is confined in a suitable vessel at subatmospheric pressure 0.027 Pa to 0.266 Pa, suitably 0.054 Pa (0.2 mtorr to 2 mtorr, suitably 0.4 mtorr, where mtorr means millitorr). A plasma is generated in the low pressure argon gas to form a suitable concentration of positively charged argon ions. The workpiece is immersed in the plasma and is in electrical contact with a suitable high voltage pulser. The pulser apparatus applies pulses of negative electrical potential to the workpiece at a repetition rate of, for ex-



ample, about 100 to 3000 Hz, suitably 2000 Hz.

[0010] The pulses are suitably of 10 to 20 ms duration. The high voltage pulser is preferably adapted to apply essentially square wave form voltage pulses so that the workpiece is very rapidly but momentarily charged to a suitable negative voltage. During each high voltage application to the workpiece, the positive argon ions in the surrounding plasma are uniformly accelerated to all surfaces of the target with an impact kinetic energy governed by the magnitude of the pulse. The high voltage pulses applied to the workpiece in combination with the positive argon ions in the plasma sputter clean the workpiece by driving off oxygen atoms from the surface. A total electrical potential of about 1 to 10 kV applied to the workpiece as negative pulses is suitable for this purpose.

[0011] In an alternative practice, a plasma is generated around the workpiece by driving the workpiece with a radio frequency signal of 100 W to 5000 W, suitably 1000 W. This produces a concentration of positive argon ions around the workpiece. The rf signal also produces a negative dc self-bias on the workpiece of 500 V to 2000 V, suitably 1000 V, which accelerates the positive argon ions toward the workpiece surface, bombarding the surface and sputtering off oxide material. This dc self-bias is hereinafter referred to as a constant negative electrical potential.

[0012] After the oxygen atoms are sputtered from the surfaces of the workpiece, plasma generation is stopped, argon is evacuated from the vessel and the vessel is backfilled with a carbon-containing gas suitable for carbon implantation. Methane and/or acetylene are preferred for this application. Again, a low pressure (suitably a few tenths of a mtorr) (1 mtorr being 0.133 Pa) plasma is generated within the carbon-containing gas, which now consists of positive hydrogen-containing carbon ions. The workpiece is fully immersed in this plasma. Again, the high voltage pulser activates the workpiece by the application of high frequency, short duration pulses of negative potential at a voltage on the order of tens of kilovolts suitable for ion implantation. The effect of this step is to implant carbon ions into the surface of the workpiece to a suitable shallow depth of the order of 75 to 150 nm. The carbon ion implantation leads to formation of aluminum carbide and silicon carbide. A byproduct of this implantation step is the codeposition of a thin layer of graphitic material on the surface above the implanted carbon species.

[0013] The next step of the process involves the removal of the graphitic material. The removal of the graphitic material is necessary for the formation of an adherent coating of diamond-like carbon. This step is accomplished by the evacuation of carbon-generating plasma gas from the vessel and again backfilling with argon gas or other suitable gas that is chemically inert to the workpiece. The pressure of the plasma and the energy and frequency of electric potential pulses (or the magnitude of the dc self-bias) applied to the workpiece

are essentially the same as in the oxygen removal step. This step serves to bombard the surface with positive argon ions and to sputter the surface at an energy level of about 500 eV to 10 keV so as to sputter the graphitic material from the surface and expose the desired surface of the aluminum alloy with its shallowly-embedded aluminum carbide and silicon carbides.

[0014] The final step involves the removal of argon gas from the vessel and backfilling with acetylene and/or methane for the deposition of the amorphous hydrogen-containing carbon. Since this is a deposition step and not an implantation step, lower energy levels are suitable at a plasma pressure of about 0.266 Pa to 9.31 Pa (2.0 to 70 mtorr). A hydrogen-containing amorphous carbon layer is built up on the surface to a desired thickness of, e.g., about 1 to 10 micrometers to complete the process. The coating is adherent, wear and scuff resistant and "slippery".

[0015] Thus, the process involves successive immersion of workpieces within different plasma compositions which treat all surfaces of the workpiece(s) while retained in plasma treatment vessels. Surface oxides are removed, carbon implanted to form carbides, an extraneous graphitic layer is removed, and a tightly adherent and extremely wear-resistant diamond-like carbon coating is formed. Thus, one or many workpieces can be introduced into and treated in the same or interconnected plasma vessel system to simultaneously and efficiently form the adherent carbon coating on all surfaces of all workpieces. When a large number of workpieces are treated simultaneously, it is preferred to apply high voltage pulses to the workpieces and to generate the plasma around the workpieces by a separate means.

[0016] Other objects and advantages of the invention will be more fully appreciated from a detailed description thereof which follows. Reference will be made to the drawing.

Brief Description of the Drawing

[0017] The drawing figure schematically depicts in cross section a plasma source ion implantation vessel with a high voltage pulser and other related equipment suitable for a preferred practice of the process.

Description of an Embodiment of the Invention

[0018] The practice of the invention utilizes a suitable plasma immersion ion treatment apparatus. The Figure of the drawing depicts schematically and in partial cross-section such apparatus and auxiliary equipment at 10. The apparatus system 10 includes a suitable vessel 12 which may be a cubical box (as shown) or a cylinder. Vessel 12 has a door (not shown) for introducing and removing workpieces and for maintenance of the interior chamber 14. The vessel 12 is constructed so as to be air tight and capable of sustaining low pressures (i.e., vacuum) as low as 1.33×10^{-4} Pa (1 microtorr) in its



inner chamber 14. In order to provide such low pressures, a suitable vacuum system 16 is connected through exhaust line 18 to chamber 14.

[0019] All of the walls 20 of vessel 12 are electrically interconnected and electrically maintained at a common potential. The vessel may be grounded as indicated at 22.

[0020] A workpiece carrying stage or platform 24 is mounted on post 26, which electrically insulates platform 24 from the vessel walls 20. Provision is made to cool the stage 24 such as by circulating deionized water or other electrically insulating cooling fluid through coils indicated schematically at 28. In the operation of the system 10, workpieces 30 such as aluminum A390 alloy piston heads will be placed on stage 24.

[0021] Provision is made for the admission of a variety of gases into chamber 14. Thus, a plurality of gas lines indicated at 32, 34 and 36, respectively, lead from separate gas sources (not shown) to common line 38 and through needle valve 40 into chamber 14. In the practice of the process as will be described in more detail below, gases such as argon (through line 32), methane (through line 34) and acetylene (through line 36) will be bled through needle valve 40 into chamber 14 after evacuation by vacuum system 16 to a suitable working gas pressure. Once one of such gases has been introduced into chamber 14, a plasma is generated in the gas by means of a suitable plasma generator such as a radio frequency generator indicated schematically at 42. The plasma generator is employed to generate respectively positive argon ions, positive methane ions, positive acetylene ions, positive ions of the partially or completely disassociated constituents of these gases, or the like for treatment of workpieces 30. Depending upon the specific operation being performed, the working pressure of the gas or plasma within the vessel will typically and suitably lie within the range of 0.013 Pa to about 13.3 Pa (0.1 mtorr to about 100 mtorr). Such pressure is maintained through the operation of the vacuum system and the bleeding of the gas into the chamber.

[0022] Each plasma completely fills the chamber and completely immerses workpieces 30. In order to accelerate the positive ions in the plasma toward workpieces 30, high voltage, short duration negative potential pulses are continually applied to the workpieces. This is suitably accomplished by employment of a high voltage pulser 43, which is electrically connected through lead 44 to work stage 24. The work stage 24 is electrically conductive and conducts the high voltage pulses to workpieces 30. However, lead 44 is electrically insulated from wall 20, and the stage 24 is likewise electrically insulated from the vessel by post 26. The pulser 43 is capable of generating high voltages as will be described in the respective operating steps below. For the implantation step, the pulses are suitably of short duration, typically in the range of 10 to 30 microseconds, and continually applied at a frequency of several kilohertz. For sputtering and deposition steps, the pulses are of high

duty cycle, typically in the range of 20 percent to 95 percent. Desirably, the wave form of the voltage pulses is as square as possible, especially during the implantation and deposition steps. This, of course, means a very fast rise to the applied voltage level, maintenance at that level during the desired time, and then a very rapid fall from the voltage level. The purpose of the pulses is to accelerate positive ions from the plasma toward and against the surfaces of workpieces to obtain sputtering for cleaning, implantation or coating as will be described at the desired energy level. To the extent that the wave form departs from its desired square shape, ions with undesired kinetic energies are accelerated toward the workpieces and produce results that might not be desirable, especially during the implantation and deposition steps. The process steps each rely on the suitable kinetic energy of the plasma ions and not upon thermal diffusion or other thermodynamic equilibrium mechanism. However, thermal diffusion may be used as an additional control mechanism for achieving deeper penetration of ions during the implantation process.

[0023] In an alternative embodiment, an rf generator (not shown), which may or may not be the same physical piece of equipment as rf generator 42, can also be used to produce a dc self-bias on workpieces 30 for sputtering or deposition steps. Such rf generator would be connected to work stage 24 via lead 44 and/or other suitable means not depicted in the figure.

[0024] A general description of method and apparatus for plasma source implantation may be found in U.S. Patent 4,764,394.

[0025] This process has been utilized in one example to apply hard, adherent carbon coatings to aluminum alloy A390 workpieces, including the skirt portions of pistons made from such alloys. The nominal composition of the 390 alloy is, by weight, 17 percent silicon, 0.8 percent iron, 4.5 percent copper, 0.050 percent manganese, 0.580 percent magnesium, 0.040 percent chromium, 0.950 percent zinc, 0.1 percent titanium and the balance substantially all aluminum. Piston skirts cast from such alloys thus would contain a surface region that would contain not only atoms of the respective elements of the composition but also oxides that have formed on the surface with aluminum and silicon.

[0026] In the case of the aluminum alloy workpieces, it is necessary to remove oxygen atoms from the surfaces before proceeding further with the process. This oxide decomposition process may not be necessary with other workpiece materials. The oxide removal can be carried out by any suitable cleaning process. However, since subsequent process steps are carried out in an ion plasma implantation vessel 12, it is preferred to confine the workpieces in the vessel for all of the processing steps.

[0027] Thus, one or more workpieces such as aluminum alloy 390 pistons are introduced into vessel 12 and the chamber 14 evacuated to a very low pressure to remove atmospheric gases from the chamber. The pres-



sure is suitably reduced to about 1.33×10^{-4} Pa (1 microtorr) (10^{-6} torr). With vacuum system 16 still running, argon gas through line 32 is then slowly bled into the chamber to reach a stable operating argon gas pressure of about 0.054 Pa (0.4 mtorr). A suitable range for this argon sputter cleaning step is from 0.027 Pa to 0.266 Pa (0.2 mtorr to 2 mtorr). The selected pressure is dependent upon the energy intended to be applied to the workpieces. Once the argon pressure has been stabilized at, for example, 0.054 Pa 0.4 mtorr, the plasma generator 42 is started and the glow of the plasma comprising electrons and positive argon ions is apparent through a viewing window (not shown) in vessel 12. Upon the establishment of the argon positive ion-containing plasma, the high voltage pulser 43 is activated at a repetition rate of several kilohertz and voltage pulses of about 1.2 kV. In the case of the argon plasma, this produces argon ion energies of about 1.2 keV. In general, a voltage level of 1 to 10 kV is suitable for sputter cleaning.

[0028] In an alternative method, an rf generator (not shown) is connected to work stage 24 (in place of the depicted plasma generator 42 and pulser 43) through lead 44. When such rf generator is started, an argon plasma with positive argon ions is established. Also, a dc self-bias of about 1000 V is produced on the workpiece to induce bombardment of the workpiece with a flux of 1000 eV argon ions.

[0029] Either of the two above-described methods leads to a flux of argon ions that sputters off oxygen atoms. A sputtering time of the order of 60 minutes is found to be sufficient for suitable removal of oxides from the surface region of the aluminum alloy workpieces. During the sputtering operation, cooling deionized water or other electrically insulating cooling fluid is circulated through cooling passages 28 in the workpiece platform 24 in order to remove heat from the workpieces generated by the sputtering.

[0030] The first principal step in the subject process is the implantation of carbon ions into the surface of the cleaned workpiece(s) 30. The plasma generator 42 is inactivated, as is the high voltage pulser 43. The flow of argon gas is shut off, and argon gas is pumped from the chamber 14 by the vacuum system 16. Methane gas or other suitable hydrocarbon is introduced into the chamber as through line 34. The pressure of methane gas is suitably in a range from about 0.027 Pa to 0.798 Pa (0.2 to 6 mtorr), and the plasma is again re-established through utilization of plasma generator 42. High voltage pulses at a repetition rate of several kilohertz and at approximately 20 kV are applied to the workpieces by pulser 43 through the workpiece stage 24. A suitable voltage level for this carbon implantation step is in the range of about 5 kV to 40 kV. At the application of 20 kV pulses, the implantation of the positive carbon and hydrocarbon ions into the workpiece surface is continued until a dosage of about 2 to 5×10^{17} ion/cm² is obtained. Approximately one hour is required to obtain a suitable

implantation level of the carbon or hydrocarbon ions into the surface to a dose of 2 to 5×10^{17} ion/cm², although this depends upon the workpiece surface area and implant current capacity of high voltage pulser 43. If the pressure or the repetition rate is changed, then the processing time is also changed. The effect of the implantation is to form aluminum carbides and silicon carbides which are apparently uncrystalline in nature. However, it is particularly the silicon carbide moieties present in the thin surface region of the workpieces which ultimately provide the adherent substrate for the final carbon deposit.

[0031] It has been found, due apparently to the inability to obtain a perfectly square voltage wave form, that in addition to the carbon ions that are implanted into the workpiece, a thin layer of extraneous carbon apparently in the form of graphite is deposited on the surface. It is believed that the depth of the implanted carbon is of the order of 20 to 120 nm. The superficial layer of amorphous carbon is apparently much less than the thickness of the implanted carbon.

[0032] In order to form a suitably adherent carbon deposit on the carbon implanted surface, it is necessary to remove the graphitic layer. This is accomplished by shutting down the plasma generator 42 and the high voltage pulser 43, pumping the methane gas from the chamber 14 and backfilling the chamber with argon gas as from line 32. An argon pressure of about 0.054 Pa (0.4 mtorr) 0.027 Pa to 0.266 Pa (suitably 0.2 mtorr to 2 mtorr) is maintained in the chamber as in the previous argon sputter step. Plasma generation is recommenced as is application of 1.2 kV negative impulses to the workpiece by actuating the high voltage pulser 43. The effect of the high voltage pulses applied to workpiece 30, which is immersed in the argon ion plasma, is to accelerate argon ions against the graphite-coated surfaces. After a period of about 5 to 10 minutes, the sputtering by the argon ions suitably removes the graphitic deposit from the surface of the carbon implanted workpiece. The plasma generator 42 and voltage pulser 43 are shut down and argon gas pumped from the chamber.

[0033] In an alternative practice to the use of the voltage pulser 43, an rf generator (not shown) is connected to work stage 24 as through lead 44. As described above, activation of the rf generator produces an argon plasma in an argon gas-filled chamber and produces a suitable dc self-bias on workpiece 30 to promote sputtering of the graphite deposit from the surface of the workpiece.

[0034] The chamber 14 was then backfilled with acetylene in preparation for the deposit of a hard adherent amorphous carbon film on the surface of the carbon implanted workpiece. The gas pressure of the acetylene is suitably in the range of 0.266 Pa to 9.31 Pa (2 to 70 mtorr). The purpose of this step is to deposit carbon on the surface, not to implant it. Accordingly, lower energy levels are employed. While acetylene is used in this example, other low molecular weight hydrocarbon gases



such as methane are suitable. An acetylene pressure of 0.60 Pa (4.5 mtorr) is employed and 600 volt negative pulses (30 msec duration) are applied to the workpieces with a duty cycle of 20 percent to 95 percent.

[0035] Alternatively, an rf generator (not shown) is used to generate an acetylene plasma and produce a negative dc self-bias of 600 V on workpiece 30. This process was continued, in the case of dc self-bias, for about 150 minutes, during which time a uniform layer of adherent, hard, hydrogen-containing carbon was formed that was about 5 micrometers in thickness. Depending upon the application of the workpiece in which the coating was formed, in general it is felt that carbon coatings 1 to 5 micrometers or higher, for example, 10 mm, are suitable.

[0036] The purpose of the above coating process with respect to aluminum pistons was to determine whether pistons thus coated could be operated, particularly in cold start situations, in an engine utilizing a cast aluminum alloy engine block without any liner. During cold start situations, there is a dearth of oil on the surface of the cylinder walls, and it is not uncommon for the aluminum pistons to engage the aluminum cylinder walls without any lubricant film between them. In normal operation, it is found that scuffing occurs between the aluminum piston and the aluminum wall. That is to say, aluminum metal is transferred from the cylinder wall to the piston, which promotes wear and tear in the engine and is unsuitable for long-term engine life. However, bench tests and engine tests have indicated that aluminum alloy pistons provided with a carbon coating 5 micrometers or more in thickness as produced by this process ran satisfactory during engine cold start without scuffing. Of course, it is known that diamond-like carbon coatings can provide desirable wear properties to many different substrates. The subject high voltage pulser process forms adherent coatings simultaneously on many workpieces all with complex shapes in a practice suitable for high volume production.

[0037] The precise chemical and metallurgical nature of the carbon coatings has not been fully analyzed. In general, the coatings are amorphous, although they may contain some nanometer-size crystals of carbon. The coatings also contain some hydrogen, probably about one hydrogen atom per three or so carbon atoms. Thus, in general the coatings can be characterized as amorphous to nanocrystal carbon that contains a minor portion of hydrogen. Sometimes these coatings are referred to as diamond-like carbon coatings. They are not diamond in constitution, but they do contain an appreciable fraction of sp^3 bonds between their carbon atoms. The coatings display high hardness values, and they provide lubricity in friction applications.

[0038] It has been observed that when other metals, synthetic plastics or glass are placed in the subject plasma source ion implantation apparatus, they are likewise coated with the hard amorphous carbon in the same manner as the aluminum alloy coated workpieces de-

scribed above. Such materials have been used in connection with the fixtures for test workpieces, and when they are not electrically insulated from the high voltage pulser, they experience the same processing conditions as the workpieces and they are likewise coated. It is clear that the subject process of implanting carbon into a workpiece, sputter removing the extraneous graphitic carbon that is coincidentally formed during the carbon implantation, and then applying an amorphous carbon coating is of general application to a wide range of workpiece materials.

[0039] This process basically relies solely upon the kinetic energy of the ions in the plasma for its execution. However, when the ions impact the workpiece, they do promote heating. For this reason, the workpiece is cooled to maintain it at a suitable temperature. For example, it is not preferable to have a significant amount of diffusion of the implanted or coated ions into the workpiece.

[0040] An advantage of the subject process is that all unmasked surfaces of three-dimensional workpieces can be implanted or coated uniformly and at the same time. The practice is not limited by the disadvantages of line-of-sight treatments. Furthermore, if desired, the workpieces can be treated continually and automatically in a single vessel or system without removal to the ambient.

[0041] While this invention has been described in terms of a preferred embodiment thereof, it will be appreciated that other forms could readily be adapted by one skilled in the art. Accordingly, the scope of this invention is to be considered limited only by the following claims, in which further details may be seen.

Claims

1. A method of forming an adherent, hard carbon coating on an article composed of a material receptive to carbon ion implantation, characterized in that said process comprises:

immersing said article in a first plasma atmosphere containing positive carbon ions and accelerating said ions against surfaces of said article to implant carbon ions into said surfaces and, coincidentally, form an overlying deposit of carbonaceous material,

thereafter immersing the article in a positive ion containing plasma of a gas chemically inert with respect to the article and accelerating positive ions against said deposit on said article to bombard said carbonaceous deposit with said ions and thereby remove it from carbon-implanted surfaces, and

thereafter immersing said article in a plasma containing positive carbon ions and accelerating said positive ions against the carbonaceous



11

EP 0 731 190 B1



12

deposit-free surfaces of said article to deposit an adherent hydrogen-containing carbon layer on said carbon-implanted surfaces.

2. A method as recited in claim 1 further characterized in that in each of said steps of immersing an article in a plasma of positive ions, the ions are accelerated against surfaces of the article by continually applying negative electrical potential pulses to said article. 5
3. A method as recited in either claim 1 or 2 further characterized in that said article to be coated is composed of a metal alloy and oxygen is removed from surfaces of the article before immersing said article in said carbon ion-containing plasma atmosphere. 10
4. A method as recited in either claim 1 or 2 further characterized in that said article to be coated is a silicon-containing aluminum alloy article and oxygen is removed from surfaces of the article before immersing said article in said carbon ion-containing plasma atmosphere. 15
5. A method as recited in claim 3 further characterized in that 20
 - (a) carbon ions are implanted into the surfaces of said article to a depth up to about 250 nanometers and form silicon carbide in said surfaces, and
 - (b) the thickness of the deposit of the adherent hydrogen-containing carbon layer on said silicon carbide-containing surfaces is in the range of about 1 μm to about 10 μm . 25

Patentansprüche

1. Verfahren zum Ausbilden einer anhaftenden harten Kohlenstoffbeschichtung auf einem Gegenstand, der aus einem Material zusammengesetzt ist, das für eine Kohlenstoffionenimplantation geeignet ist, dadurch gekennzeichnet, daß der Prozeß umfaßt, 40

der Gegenstand in eine erste Plasmaatmosphäre getaucht wird, die positive Kohlenstoffionen enthält, und diese Ionen an Oberflächen des Gegenstandes beschleunigt werden, um Kohlenstoffionen in die Oberflächen zu implantieren und gleichzeitig eine darüberliegende Ablagerung von kohlenstoffartigem Material zu bilden, 45

danach der Gegenstand in ein positive Ionen enthaltendes Plasma eines Gases getaucht

wird, das in bezug auf den Gegenstand chemisch inert ist, und positive Ionen an die Ablagerung auf dem Gegenstand beschleunigt werden, um die kohlenstoffartige Ablagerung mit den Ionen zu beschleunigen und diese dadurch von den kohlenstoffimplantierten Oberflächen zu entfernen, und

danach der Gegenstand in ein Plasma getaucht wird, das positive Kohlenstoffionen enthält, und die positiven Ionen an die von der kohlenstoffartigen Ablagerung freien Oberflächen des Gegenstandes beschleunigt werden, um eine anhaftende wasserstoffhaltige Kohlenstofflage auf den kohlenstoffimplantierten Oberflächen abzulagern.

2. Verfahren nach Anspruch 1, ferner dadurch gekennzeichnet, daß bei jedem der Schritte zum Eintauchen eines Gegenstandes in ein Plasma aus positiven Ionen die Ionen an Oberflächen des Gegenstandes durch kontinuierliches Anlegen von Impulsen mit negativem elektrischen Potential an den Gegenstand beschleunigt werden.

3. Verfahren nach einem der Ansprüche 1 oder 2, ferner dadurch gekennzeichnet, daß der zu beschichtende Gegenstand aus einer Metallegierung zusammengesetzt ist, und Sauerstoff von den Oberflächen des Gegenstandes vor dem Eintauchen des Gegenstandes in die kohlenstoffionenhaltige Plasmaatmosphäre entfernt wird.

4. Verfahren nach einem der Ansprüche 1 oder 2, ferner dadurch gekennzeichnet, daß der zu beschichtende Gegenstand ein Gegenstand aus einer siliziumhaltigen Aluminiumlegierung ist, und Sauerstoff von den Oberflächen des Gegenstandes vor dem Eintauchen des Gegenstandes in die kohlenstoffionenhaltige Plasmaatmosphäre entfernt wird.

5. Verfahren nach Anspruch 3, ferner dadurch gekennzeichnet, daß:

(a) Kohlenstoffionen in die Oberflächen des Gegenstandes auf eine Tiefe von bis zu ungefähr 250 Nanometern implantiert werden und Siliziumkarbide in den Oberflächen ausbilden, und

(b) die Dicke der Ablagerung der anhaftenden wasserstoffhaltigen Kohlenstofflage auf den siliziumkarbidhaltigen Oberflächen im Bereich von ungefähr 1 nm bis ungefähr 10 nm liegt.

Revendications

1. Procédé de formation d'un revêtement de carbone



13

EP 0 731 190 B1



14

adhérent et dur sur un article composé d'une matière réceptive à l'implantation d'ions carbone, caractérisé en ce que ledit procédé comprend:

l'immersion dudit article dans une première at- 5
mosphère de plasma contenant des ions car-
bone positifs, et l'accélération desdits ions con-
tre des surfaces dudit article, de manière à im-
planter des ions carbone dans lesdites surfa- 10
ces, et la formation concomitante d'un dépôt
superposé de matière carbonée,
ensuite l'immersion de l'article dans un plasma
d'un gaz contenant des ions positifs, chimique-
ment inerte par rapport à l'article, et l'accéléra- 15
tion des ions positifs contre ledit dépôt sur ledit
article, de manière à bombarder ledit dépôt car-
boné avec lesdits ions et à enlever ainsi ce dé-
pôt de surfaces contenant du carbone implan-
té, et
ensuite l'immersion dudit article dans un plas- 20
ma contenant des ions carbone positifs, et l'ac-
célération desdits ions positifs contre lesdites
surfaces dudit article, dégagées de leur dépôt
carboné, de manière à déposer une couche de 25
carbone adhérente, contenant de l'hydrogène,
sur lesdites surfaces dans lesquelles est im-
planté du carbone.

2. Procédé selon la revendication 1, caractérisé en 30
outre en ce que, dans chacune desdites étapes
d'immersion d'un article dans un plasma d'ions po-
sitifs, les ions sont accélérés contre des surfaces
de l'article en appliquant de façon continue des im-
pulsions d'un potentiel électrique négatif audit arti- 35
cle.
3. Procédé selon l'une ou l'autre des revendications 1
ou 2, caractérisé en outre en ce que ledit article à 40
revêtir est composé d'un alliage métallique, et que
de l'oxygène est retiré de surfaces de l'article avant
l'immersion dudit article dans ladite atmosphère de
plasma contenant des ions carbone.
4. Procédé selon l'une ou l'autre des revendications 1 45
ou 2, caractérisé en outre en ce que ledit article à
revêtir est un article en un alliage d'aluminium con-
tenant du silicium, et en ce que de l'oxygène est
retiré de surfaces de l'article avant l'immersion dudit
article dans ladite atmosphère de plasma contenant 50
des ions carbone.
5. Procédé selon la revendication 3, caractérisé en
outre en ce que en ce que:

(a) des ions carbone sont implantés dans les 55
surfaces dudit article, à une profondeur pou-
vant aller jusqu'à 250 nanomètres, et forment
des carbures de silicium dans lesdites surfa-

ces, et

(b) l'épaisseur du dépôt de la couche de carbo-
ne adhérente contenant de l'hydrogène sur les-
dites surfaces contenant des carbures de sili-
cium se situe dans une plage d'environ 1 μm à
environ 10 μm .

